

PRODUCT DATASHEET

LEXAN™ 8B35 FILM

DESCRIPTION

LEXAN™ 8B35 is a one side velvet, one side matte transparent polycarbonate film. It offers high temperature resistance, excellent dimensional stability, as well as good printability without pretreatment making it very suitable for multi-layer printing for applications such as overlays, floor graphics, high-performance labels and in-mould decoration. It can be screen printed using traditional solvent based or water-based inks, as well as UV or infrared drying inks and offers ease of processing for thermoforming, embossing, die-cutting, hydroforming and bending. The velvet texture offers mar resistance, and can be used over light-emitting devices (LEDs)

TYPICAL PROPERTY VALUES*

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	8500	ISO 527	MPa	62
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2100
Tensile Elongation at Break	ASTM D882	%	100-156	ISO 527	%	100
Gardner Impact Strength at 0.03" (0.75 mm)	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	245
Propagation	ASTM D1922	g/mil	30-55		kN/m	10-20
Puncture Resistance (Dynatup) 0.25mm	ASTM D3763	ft-lb	455		J	24.7
Fold Endurance (MIT)						
0.010" (0.25 mm)	ASTM D2176-69	double folds	60			
0.020" (0.50 mm)	ASTM D2176-69	double folds	20			
THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft2/°F/in	1.35		W/m²K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	3.2	ISO 11359	(x10 ⁻⁵ /°C)	7
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417 / D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	293		°C	145
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	252	ISO 75 Modified	°C	127
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
----------	------------------	--------------	-------	-----------------	------------	-------

PHYSICAL

Density	ASTM D792	slug/ft ³	2.3	ISO 1183	kg/m ³	1200
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Energy (1 st / 2 nd surface)	Dyne Pens	Dyne	37 / 31			
Surface Tension (1 st / 2 nd surface)	ASTM D3363	-	>44/ 38-40			
Taber Abrasion	ASTM D1044	Delta Haze	<1			

OPTICAL

Refractive Index @77°F (25°C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	80			
Yellowness Index	ASTM D1925	%	2.2			
Haze	ASTM D1003	%	102			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	See chart	ISO 2813	-	See chart
UV cutout	UV/Visual Spectroscopy	%	0.3			

*These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local POLYVANTIS representative or the POLYVANTIS Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.

™Trademark of POLYVANTIS.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.003" (0.075 mm)	-/+ 10%
0.005-0.007" (0.125-0.175mm)	-/+ 8%
0.010-0.015" (0.250-0.375)	-/+ 5%
0.020" (0.500 mm)	-/+ 3%

POLYVANTIS

www.polyvantis.com/lexan

